

YB 7005 Super silver satin

Edition: YB2018TDS

PARAMETER			SPECIFICATION		Method
Content	CAS-No.	CI-No.			
Fluorphlogopite	12003-38-2	-----	62 ~ 70	wt %	Youngbio
TiO₂	13463-67-7	77891	30 ~ 38	wt %	Youngbio
Density			2.4 ~ 3.0	g /cm ³	ISO 787-10
Bulk density			15 ~ 21	g /100ml	DIN 53466
Particle size			2-15	µm	Mastersizer2000
PH – value	10 % aqueous slurry		6 ~ 9		ISO 787-9
Loss on drying	105°C		≤0.5	wt %	ISO 787-2
Oil absorption			60 ~ 90	g oil/100g powder	ISO 787-5
Visual evaluation					
Color			conforms		Youngbio
Luster			conforms		Youngbio