

Properties - General

Melt temperature	°C	185	
Glas transition point	°C	73	
Viscosity number	ml/g	122	ISO 307
Density	g/ml	1,106	ISO 1183
Humidity absorption (20/65%)	%	3,5-4,5	
Water absorption	%	15-17	
Viscosity solution 20% in n-prop:wasser=8:2	mPa s	1200	DIN 53019
Hazen color 20% in n-prop:wasser=8:2		<100	
Oxygen permeability	cm ³ 100mm/m ² d bar	15	